

MONTICOLOR

Yarn Technical Data Sheet

APRICOT 3/50

Last update: 17.07.2020

| | | |
|------------------------------------------|---------------------|---------------|
| Count | Gauge | |
| Ne 30/3 - Nm 3/50 | 12 | |
| Shade Card | | |
| SOFFIO DI LANA 1.3 | | |
| Description | Raw | Colors |
| Cotton wool | yes | 60 |
| Kg Minimum | Availability | |
| 3 | fast service | |
| Customer Color | | |
| yes | | |
| Composition | | |
| 40% Merino wool - 60% Makò combed cotton | | |

| | |
|-----------------------------------------------|--------------------|
| Pilling (ISO 12945-1:2002) | |
| 3/4 | |
| Unit Weight (g/m2) | Wastage (%) |
| 215 | 4 |
| Conventional standard conditioning (%) | |
| 12,20 | |
| Average applied conditioning (%) | |
| 5,00 | |
| QR Code | |




Stock for sampling

Suggested International Symbols



End Uses



Certifications



| Requirements | Discharge on cotton | Color changing |
|------------------------------------------------------|---------------------|----------------|
| Color fastness to washing in water 40° (ISO 105/C06) | 4 | 4 |
| Color fastness to dry cleaning (ISO 105/D01) | 4 | 4 |
| Color fastness to acid-basic sweat (ISO 105/E04) | 4 | 4 |
| Color fastness to rubbing (ISO 105/X12) | | |
| Dry | 4 | |
| Wet | | |
| Light | 3/4 | |
| Medium-dark | 2/3 | |
| Melange light | | |
| Melange medium-dark and grey | | |
| Color fastness to light (ISO 105/B02) | | |
| Light | | 3/4 |
| Medium-dark | | 4 |

Special Cares

Shade card solid colors should be considered just as an indication.

SPECIAL ATTENTION

- The yarn is in compliance with the REACH Regulation (1907/2006).
- If this yarn is used for stripes with white or contrasting colors, please specify with the order proposal in order to verify the possibility of doing it.
- We recommend to test different colors which can be representative for bulk production. Different colors may require adjustments relating knitting and finishing process.
- Knitting: please ensure a perfect functioning of the machine. Use of electronic feeded machines is highly recommended. When starting to knit a different batch it is recommended to check new outcome and se the tightness of needles to adjust possible differences.
- No claims can be accepted on knitted panel for more than kg 5 of each dye lot, and in no case on finished garments.