



Yarn Technical Data Sheet

ADAPTO 20000


Last update: 22.11.2023

Count	Gauge
Nm 20000	12
Composition	
90% Lyocell LF - 10% PBT polyester	
Shade Card	
ADAPTO 3.0	
Description	Colors
Botanic stretch	24
Customer Color	
yes	
Availability	Raw
on request	yes
Kg Minimum	
20	

Pilling (ISO 12945-1:2002)	Flammability
4	
Unit Weight (g/m2)	Wastage (%)
225	4
Conventional standard conditioning (%)	
11,73	
Average applied conditioning (%)	
3,00	
Suggested International Symbols	



End Uses



Requirements	Discharge on cotton	Color changing
Color fastness to washing in water 40° (ISO 105/C06)	4	4
Color fastness to dry cleaning (ISO 105/D01)	4	4
Color fastness to acid-basic sweat (ISO 105/E04)	4	3
Color fastness to rubbing (ISO 105/X12)		
Dry	4	
Wet		
Light	3/4	
Medium-dark	2/3	
Black		
Melange light		
Melange medium-dark and grey		
Color fastness to light (ISO 105/B02)		
Light		3/4
Medium-dark		4

Certifications



Special Cares

Shade card colors should be considered just as an indication. Due to the different color absorption between polyester and Lyocell, colors might appear not perfectly equalized in shade. To avoid creasing and wrinkling effects it is recommended to dry the knitted pannels with a humidity level above average and iron immediately after drying. We recommend to use more threadguides. Yarn not suitable on machines for whole garment. TENCEL™ is a trademark of Lenzing AG.

SPECIAL ATTENTION

- The yarn is in compliance with the REACH Regulation (1907/2006).
- If this yarn is used for stripes, with white or contrasting colors and/or for wholegarment please specify with the order proposal, in order to verify the possibility of doing it.
- We recommend to test different colors which can be representative for bulk production. Different colors may require adjustments relating knitting and finishing process.
- Knitting: please ensure a perfect functioning of the machine. Use of electronic feeded machines is highly recommended. When starting to knit a different batch it is recommended to check new outcome and se the tightness of needles to adjust possible differences.
- No claims can be accepted on knitted panel for more than kg 5 of each dye lot, and in no case on finished garments.
- The RAW-WHITE variant has a different behavior compared to the dyed colors as it didn't undergo the dyeing process and can therefore show variations in shade from one lot to another.