



Yarn Technical Data Sheet

INTRECCIO 1100 Last update: 19.01.2024

Count Gauge
Nm 1100 3

Composition

100% Mercerized cotton

Shade Card

INTRECCIO-HELIX 3.1

DescriptionColorsSculpted Cable'40

Customer Color

yes from TOP MERCERIZED shade card, no melange col

Availability Raw on request yes

Kg Minimum

4

Pilling (ISO 12945-1:2002)	Flammability	
	Class 1 - not inflame	
Unit Weight (g/m2)	Wastage (%)	
125	5	

Conventional standard conditioning (%)

10,50

Average applied conditioning (%)

4,50

Suggested International Symbols











End Uses

Weft



Requirements	Discharge on cotton	Color changing
Color fastness to washing in water 40° (ISO 105/C06)	4	4
Color fastness to dry cleaning (ISO 105/D01)	4	4
Color fastness to acid-basic sweat (ISO 105/E04)	4	4
Color fastness to rubbing (ISO 105/X12)		
Dry	4	
Wet Light	3/4	
Medium-dark	2/3	
Black		
Melange light		
Melange medium-dark and grey		
Color fastness to light (ISO 105/B02)		
Light		3/4
Medium-dark		4

Certifications





Special Cares

- The yarn is in compliance with the REACH Regulation (1907/2006).
- If this yarn is used for stripes, with white or contrasting colors and/or for wholegarment please specify with the order proposal, in order to verify the possibility of doing it.

 We recommend to test different colors which can be representative for bulk production. Different colors may require adjustments relating knitting and finishing process.
- Knitting: please ensure a perfect functioning of the machine. Use of electronic feeded machines is highly recommended. When starting to knit a different batch it is
- Nilling, please elisting a period unitationing of the maturine, observed in the maturine, obse
- No claims can be accepted on knitted panel for more than kg 5 of each dye lot, and in no case on finished garments.
- The RAW-WHITE variant has a different behavior compared to the dyed colors as it didn't undergo the dyeing process and can therefore show variations in shade from one lot to another.