MONTICOLO

Yarn Technical Data Sheet



ORGANIC SENSE 30/3

Last update: 26.06.2023

ORGANIC SENSE 30/3						Last update	9: 20.00.2023
Count		Gau	ige	Pilling (ISO 12945-1	:2002)	Flammabil	ity
Ne 30/3 - N	lm 3/50	12	2	3			
Composition				Unit Weight (g/m2)		Wastage (%)	
90% organic cotton - 10% cashmere				4			
				Conventional standard conditioning (%)			
Shade Card			9,29				
ORGANIC SENSE 3.0				Average applied conditioning (%)			
Description	Description		ors	3,00			
Rewarding attitude		25	5	Suggested International Symbols			
Customer Color				30°/ (P)	\mathbf{A}	\boxtimes	Ţ
yes							
Availability		Raw	•	End Uses			
on request			S	Tricot			
Kg Minimum							
8				(THA)			
	RequirementsColor fastness to washing in water 40° (ISO 105/C06)Color fastness to dry cleaning (ISO 105/D01)Color fastness to acid-basic sweat (ISO 105/E04)Color fastness to rubbing (ISO 105/X12)		Discharge on cotton	Color ch	anging		
			4		4		
			′D01)	4		4	
			105/E04)	3/4	:	3/4	
)				
	Dry			4			
	Wet	Light		3/4			
		Medium-dark		2/3			
		Black		2/3			
		Melange light					
		Melange medium-dark a	and grey				
	Color fastness to light (ISO 105/B02)						
		Light				3	
		Medium-dark				4	

Certifications



Special Cares

Color shade reproducibility might undergo certain limitations due to GOTS regulation restrictions. The occasional presence of natural darker fibers visible on light colors and lighter fibers visible on dark colors is a typical feature due to the fibers employed.

SPECIAL ATTENTION

- The yarn is in compliance with the REACH Regulation (1907/2006).

- If this yarn is used for stripes, with white or contrasting colors and/or for wholegarment please specify with the order proposal, in order to verify the possibility of doing it. - We recommend to test different colors which can be representative for bulk production. Different colors may require adjustments relating knitting and finishing process. - Knitting: please ensure a perfect functioning of the machine. Use of electronic feeded machines is highly recommended. When starting to knit a different batch it is

recommended to check new outcome and se the tightness of needles to adjust possible differences - No claims can be accepted on knitted panel for more than kg 5 of each dye lot, and in no case on finished garments.

- The RAW-WHITE variant has a different behavior compared to the dyed colors as it didn't undergo the dyeing process and can therefore show variations in shade from one lot to another.